

Sublitex Quality Control
Laboratory and R&D:

**ACCELERATED
WEATHERING TEST**

Decotrans[®]
Alu

**TEST REPORT
NUMBER:**

RPA_1511_2DA



**TEST:
XENON TEST**

Apparatus: Q-SUN XE-3 HS

**DECORATION :
99061-201
POWDER COATING:
PC-111**

**TOTAL DURATION:
2000 HOURS**

SAMPLE EVALUATION:

RESIDUAL GLOSS

108%

**COLOUR VARIATION
 ΔE**

1.63

GREY SCALE

4



EXPOSED AREA

**FINAL RESULT:
PASS**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, accelerated weathering test is only one of the conditions necessary for the evaluation of the finished product. For a final assessment see further analysis on natural exposure in Florida.