

Sublitex Quality Control
Laboratory and R&D:

**ACCELERATED
WEATHERING TEST**

Decotrans[®]
Alu

**TEST REPORT
NUMBER:**

RPA_1932_1DA



**TEST:
XENON TEST**

Apparatus: Q-SUN XE-3 HS

**DECORATION :
9Y006
POWDER COATING:
PGU22 301**

**TOTAL DURATION:
2000 HOURS**

SAMPLE EVALUATION:

RESIDUAL GLOSS


57%

**COLOUR VARIATION
 ΔE**

1.32

GREY SCALE

4/5



EXPOSED AREA

FINAL RESULT:

PASS

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, accelerated weathering test is only one of the conditions necessary for the evaluation of the finished product. For a final assessment see further analysis on natural exposure in Florida.