



Product Description ENG

Date 05.10.2022

DESCRIPTION

Polyester film (PET) printed with rotogravure, used for the finishing of :

- Aluminum
- Steel
- Stainless steel
- Hot Galvanized Steel
- Cold Rolled Steel
- Electrogalvanised Steel

Available for internal and external use (UV-stabilized film)

A specific base coating is required.

SUPPORT

- Print width: max 1500 mm (1860 mm upon request)
- Film thickness: 15 - 20 µm
- Base weight: 21-28 g/m²
- Core diameter: 75 to 150 mm
- Roll diameter: 200 to 500 mm
- Roll length max : 4000 m
- Weight : max 200 kg

PRINTING

In rotogravure using solvent based inks.

BRIGHTNESS

Matte (20 gloss) or High Gloss (>90 gloss)

APPLICATION SYSTEMS

It is possible to apply the product with calendering, and the optimum adhesion temperature can vary from 140°C to 190°C depending on the type of coil, type of base coating of the same.

To optimize the operating conditions we recommend running tests in production, considering the transfer process of the film and the support to ennoble.



Cap. Soc. Euro 1.000.000 i.v.
Nr. R.E.A. CN-313093
Cod. Fisc. / P.I. IT
03737080048

Società con unico socio

Società soggetta all'attività di
direzione e coordinamento
di Miroglio S.p.A.

Sublitex s.r.l.
Strada Tagliata 25
12051 Alba CN - Italy
sublitex@miroglio.com
t. (+39) 0173 298741
f. (+39) 0173 298220

Sede legale:
Via S. Barbara 11
12051 Alba CN - Italy
sublitex.com

QUALITY AND R&D

Internal quality check are performed through application of comparative test with the master(first standard production) for the evaluation of the color shade on the decorated surface.

Internal analysis and quality checks :

- Artificial weathering (UV-stabilized film) in accordance with :
 - UNI EN ISO 4892-2 (Xenon test with solar filter)
 - UNI EN ISO 4892-3/2006 (QV-B @314 nm)

External quality checks for UV-stabilized film (outdoor use)

- ASTM 4141 (EMMAQUA/Q-Trac - natural sunlight concentrator)
- ASTM -D 1014 (FLORIDA TEST)
- ISO 7724/3 – 1984 (QV-A @ 314 nm); evaluation of
 - ISO 4628/2 (Blistering)
 - ISO 4628/3 (Rusting)
 - ISO 4628/2 (Cracking)
 - ISO 4628/5 (Flaking)
 - ISO 105 A02 (Change of colour)

Test conducted @ "Stazione Sperimentale per le Industrie degli Oli e dei Grassi" (SSOG).

The areas of responsibility of the SSOG are specified in:

- D.Lgs. 2 February 1919, n.637;
- D.Lgs. 29 October 1999, n.540;
- D.Lgs. 23 February 2001, n.71.

	<i>Blistering</i> [ISO 4628/2]	<i>Rusting</i> [ISO 4628/3]	<i>Cracking</i> [ISO 4628/2]	<i>Flaking</i> [ISO 4628/5]
Artificial weathering (Q-UVA @ 340 nm – 3000h) [UNI EN ISO 7724/3 – 1984]	Absent	Absent	Absent	Absent
Change of color [ISO 105 A02] after artificial weathering [ISO 7724/3 – 1984]	After 1000 h	After 2000 h	After 3000 h	
	5/5	5/5	4/5	

Texcover quality checks for indoor use (Independent laboratory accredited)



Cap. Soc. Euro 1.000.000 i.v.
Nr. R.E.A. CN-313093
Cod. Fisc. / P.I. IT
03737080048

Società con unico socio

Società soggetta all'attività di
direzione e coordinamento
di Miroglio S.p.A.

Sublitex s.r.l.
Strada Tagliata 25
12051 Alba CN - Italy
sublitex@miroglio.com
t. (+39) 0173 298741
f. (+39) 0173 298220

Sede legale:
Via S. Barbara 11
12051 Alba CN - Italy
sublitex.com

Coefficient of friction (static)	ASTM-D 1894	0.4																																																						
Gloss	DIN 67530	180 Gloss @ 20° 100-120 Gloss @ 60° * * value depending on the design																																																						
Adhesion after drawing	ECCA T6	No loss of adhesion																																																						
Resistance to bending	ECCA T7	0.5T																																																						
Resistance to rapid deformation	ASTM D 2794-93	Not below 140 lb*inc																																																						
Humidity chamber	ASTM D 2247-94	Unchanged after 1000 hours																																																						
Resistance to salt spray	ECCA T8	Unchanged after 500 hours																																																						
Pencil hardness	UNI 10782:99	H (Faber Castell)																																																						
Resistance to dry heat	UNI EN 12722:2009 (Min 1 - Max 5)	Unchanged until 85°C (185°F)																																																						
Artificial light fastness	ISO 105B-A02 / BS 1006A02_1978 • Temperature 55°C (131°F) • Lamp Xenon Arc • Cycle Irradiance Only • Reference International blue scale (Min 1 - Max 8)	≥ 6* * value depending on the design																																																						
Stain resistance	UNI EN 12720:2009 (Min 1 - Max 5) • 5 No defect • 4 Slight glow barely visible • 3 Visible Defect • 2 Marked defect • 1 Heavy surface degradation Time of contact in according to UNI 10944:2001 * in water solution ** Chloramines T 2,5% in water	<table> <tr> <th>Product</th><th>Result</th><th>Value</th></tr> <tr> <td>Acetic acid (10%)*</td><td>PASS</td><td>5</td></tr> <tr> <td>Acetone</td><td>PASS</td><td>5</td></tr> <tr> <td>Ammonia (10%)*</td><td>PASS</td><td>5</td></tr> <tr> <td>Citric Acid (10%)</td><td>PASS</td><td>4</td></tr> <tr> <td>Soap</td><td>PASS</td><td>5</td></tr> <tr> <td>Coffee</td><td>PASS</td><td>5</td></tr> <tr> <td>Disinfectant**</td><td>PASS</td><td>5</td></tr> <tr> <td>Ethanol 48%</td><td>PASS</td><td>5</td></tr> <tr> <td>Butyl Acetate / Ethyl Acetate 1:1</td><td>PASS</td><td>5</td></tr> <tr> <td>Olive Oil</td><td>PASS</td><td>5</td></tr> <tr> <td>Paraffin Oil</td><td>PASS</td><td>5</td></tr> <tr> <td>Sodium Carbonate (10%)*</td><td>PASS</td><td>5</td></tr> <tr> <td>Sodium Chloride (15%)*</td><td>PASS</td><td>5</td></tr> <tr> <td>Tea</td><td>PASS</td><td>5</td></tr> <tr> <td>Distilled water</td><td>PASS</td><td>5</td></tr> <tr> <td>Red wine</td><td>PASS</td><td>4</td></tr> <tr> <td>Beer</td><td>PASS</td><td>5</td></tr> </table>	Product	Result	Value	Acetic acid (10%)*	PASS	5	Acetone	PASS	5	Ammonia (10%)*	PASS	5	Citric Acid (10%)	PASS	4	Soap	PASS	5	Coffee	PASS	5	Disinfectant**	PASS	5	Ethanol 48%	PASS	5	Butyl Acetate / Ethyl Acetate 1:1	PASS	5	Olive Oil	PASS	5	Paraffin Oil	PASS	5	Sodium Carbonate (10%)*	PASS	5	Sodium Chloride (15%)*	PASS	5	Tea	PASS	5	Distilled water	PASS	5	Red wine	PASS	4	Beer	PASS	5
Product	Result	Value																																																						
Acetic acid (10%)*	PASS	5																																																						
Acetone	PASS	5																																																						
Ammonia (10%)*	PASS	5																																																						
Citric Acid (10%)	PASS	4																																																						
Soap	PASS	5																																																						
Coffee	PASS	5																																																						
Disinfectant**	PASS	5																																																						
Ethanol 48%	PASS	5																																																						
Butyl Acetate / Ethyl Acetate 1:1	PASS	5																																																						
Olive Oil	PASS	5																																																						
Paraffin Oil	PASS	5																																																						
Sodium Carbonate (10%)*	PASS	5																																																						
Sodium Chloride (15%)*	PASS	5																																																						
Tea	PASS	5																																																						
Distilled water	PASS	5																																																						
Red wine	PASS	4																																																						
Beer	PASS	5																																																						



Cap. Soc. Euro 1.000.000 i.v.
Nr. R.E.A. CN-313093
Cod. Fisc. / P.I. IT
03737080048

Società con unico socio
Società soggetta all'attività di
direzione e coordinamento
di Miroglio S.p.A.

Sublitex s.r.l.
Strada Tagliata 25
12051 Alba CN - Italy
sublitex@miroglio.com
t. (+39) 0173 298741
f. (+39) 0173 298220

Sede legale:
Via S. Barbara 11
12051 Alba CN - Italy
sublitex.com

PACKAGING

Specific for this product.

STORAGE

Keep in dry and ventilated place, protect from heat and sunlight.

PRODUCT EXPIRY DATE

1 year in the above-mentioned conditions.

NOTICE AND ADVICE

Sublitex is not responsible for unusual applications or those who have not followed the operational specifications of storage provided.

State of Art

The above information, reflect our current "State of the Art" and are disclosed by us without commitment. However possible future changes and revisions according to the evolving technology and business are possible. We invite the buyer to the verification of the information given on the basis of its technology and engineering.



Cap. Soc. Euro 1.000.000 i.v.
Nr. R.E.A. CN-313093
Cod. Fisc. / P.I. IT
03737080048

Società con unico socio

Società soggetta all'attività di
direzione e coordinamento
di Miroglio S.p.A.

Sublitex s.r.l.
Strada Tagliata 25
12051 Alba CN - Italy
sublitex@miroglio.com
t. (+39) 0173 298741
f. (+39) 0173 298220

Sede legale:
Via S. Barbara 11
12051 Alba CN - Italy
sublitex.com